10TH EUROPEAN WORKSHOP ON LIGNOCELLULOSICS AND PULP

EWLP 2008

PROCEEDINGS

KTH, Royal Institute of Technology

Stockholm, Sweden, 25-28 August 2008







THE INFLUENCE OF SOLVENT AND DERIVATIZATION ON THE ¹H NMR SPECTRAL PROPERTIES OF LIGNIN MODEL COMPOUNDS

Shiming Li¹, Knut <u>Lundquist²</u> and Jim Parkås³

 ¹ Physical Chemistry, Department of Chemical and Biological Engineering, Chalmers University of Technology, SE-412 96 Göteborg, Sweden
² Forest Products and Chemical Engineering, Department of Chemical and Biological Engineering, Chalmers University of Technology, SE-412 96 Göteborg, Sweden
³ Södra Cell AB, R&D, SE-430 20 Väröbacka, Sweden

ABSTRACT

¹H NMR spectral data for lignin model compounds are of interest in connection with the interpretation of NMR spectra of lignins recorded by 1D (¹H NMR) and certain 2D spectroscopic techniques. Derivatization influences the peak positions in the ¹H NMR spectra of lignin models to a large extent. Similarly an exchange of solvent often results in dramatic shifts of peak positions. Solvent and derivatization effects can be employed for the interpretation of lignin spectra in structural terms. This is here exemplified by results from analyses of lignin samples with respect to total hydroxyl, phenolic groups, distribution of diastereomers of arylglycerol β -aryl ethers, different types of β - β structures and occurrence of 1-aryl-2-aryloxy-1-propanone structures.

I. INTRODUCTION

¹H NMR spectra of acetate derivatives and propionate derivatives of lignin model compounds dissolved in CDCl₃, CD₃COCD₃, CD₃SOCD₃ or pyridine- d_5 have been recorded (Lundquist 1979; Lundquist *et al.* 1983; Hauteville *et al.* 1986; Lundquist and von Unge 1986; Li and Lundquist 1997). Spectra of non-derivatized model compounds in CD₃SOCD₃ or dioxane- d_8 -D₂O (5:1) solution have also been recorded (Lundquist 1981; Li and Lundquist 1994; Li and Lundquist 2001). Spectral data obtained in runs with a series of appropriate lignin models under different conditions are compared and differences in signal positions are registered. Based on the results suitable conditions for runs with lignin samples could be selected for the elucidation of particular structural features. This approach to the description of lignins in structural terms is exemplified.

II. RESULTS AND DISCUSSION

Distribution of diastereomers of anylglycerol β -aryl ethers

The positions of the H_{α} signals of acetylated *erythro* and *threo* forms of a number of lignin models of arylglycerol β -aryl ether type (Figs. 1 and 2) are listed in Table 1. The signal positions of *erythro* and *threo* forms differ significantly. This provides a basis for the elucidation of the proportions of *erythro* and *threo* forms in lignins. (Hauteville *et al.* 1986).



Figure 1. Acetylated lignin models of arylglycerol β -guaiacyl ether type



Figure 2. Acetylated lignin models of arylglycerol β -syringyl type

Table 1. ¹H NMR signal of H_{α} (δ , ppm) in acetylated arylglycerol β -aryl ethers (*erythro* and *threo* forms) in CDCl₃ solution

Erythro		Threo	
Substance	δH_{α}	Substance	δH_{α}
1e	6.04	1t	6.10
2e	6.02	2t	6.08
3e	6.01	3t	6.07
4e	6.00	4t	6.06
5e	6.04	5t	6.13
6e	6.04	6t	6.10
7e	6.03	7t	6.10

Different types of β - β structures

Data for the location of the H_{β} signal position of models of β - β type in different solvents are collected in Table 2. Acetate derivatives in CD₃COCD₃ solution permits the analysis of β - β structures in lignins (Lundquist *et al.* 1983). The H_{β} signal position of the acetates of pinoresinol (8) and syringaresinol (10) differ in pyridine- d_5 solution (Table 2) and this makes it possible to distinguish between the corresponding types of β - β structures in lignin (Lundquist and von Unge 1986).



Compound	δH _β (ppm)		
	CDCl ₃	CD ₃ COCD ₃	C5D5N
8	3.10	3.10	3.10
9	3.11	3.14	
10	3.10		3.20

Table 2. ^1H NMR signal of H_β in 8-10 dissolved in different solvents

Phenolic groups and total hydroxyl

The signals from phenolic groups are separated from other signals in lignin spectra (solvent, CD_3SOCD_3) and quantitative analysis is possible (Li and Lundquist 1994; Li and Lundquist 2001). The location of signals of guaiacyl phenols (excepting biphenyls) and syringyl phenols differ (Table 3). The proportions of these types of phenols can be determined (Li and Lundquist 1994). Total hydroxyl can be determined from spectra of propionate derivatives ($CDCl_3$) (Li and Lundquist 1997).



Table 3. ¹H NMR signal of phenolic OH in 11-15 dissolved in CD₃SOCD₃

Compound	δ Phenolic OH (ppm)	
11	8.89	
12 (erythro)	8.72	
12 (threo)	8.74	
13 (erythro)	8.13	
13 (threo)	8.11	
14	7.93 and 8.63	
15	8.21	

1-Aryl-2-aryloxy-1-propanones

From ¹H NMR spectra of models and lignins run under different conditions it can be concluded that at most traces of 1-aryl-2-aryloxy-1-propanone structures of type **16** are present in lignins. The presence of small amounts of 1-aryl-2-aryloxy-1-propanone structures of type **17** in hardwood lignins can not be excluded. Enzymic oxidation of benzyl alcohols of syringyl type leads to formation of arylketones (see e.g. Hong *et al.* 2006).



III. CONCLUSIONS

Solvents and derivatization of the samples influence the appearance of ¹H NMR spectra to a large extent. Recording of ¹H NMR spectra of lignin samples under different conditions provides structural information that is difficult to obtain by other means.

IV. REFERENCES

M. Hauteville, K. Lundquist, K. and S. von Unge, NMR studies of lignins. (7). H(1) NMR spectroscopic investigation of the distribution of *erythro* and *threo* forms of beta-O-4 structures in lignins, *Acta Chem. Scand. B* **1986**, *40*, 31-35.

F. Hong, L.J. Jönsson, K. Lundquist and Y. Wei; Oxidation capacity of laccases and peroxidises as reflected in experiments with methoxy-substituted benzyl alcohols, *Appl. Biochem. Biotechnol.* **2006**, *129*, 303-319.

S. Li and K. Lundquist, New method for the analysis of phenolic groups in lignins by ¹H-NMR spectroscopy, *Nord. Pulp Pap. Res. J.* **1994**, *9*, 191-195.

S. Li and K. Lundquist, Analysis of lignins as propionate derivatives by NMR spectroscopy, J. Wood Chem Technol. 1997, 17, 391-397.

S. Li and K. Lundquist, Analysis of hydroxyl groups by ¹H NMR spectrometry, *Nord. Pulp Pap. Res. J.* 2001, *16*, 63-67.

K. Lundquist, NMR studies of lignins. (3). Proton NMR spectroscopic data for lignin model compounds, Acta Chem. Scand. B 1979, 33, 418-420.

K. Lundquist, NMR studies of lignins. (5). Investigation of nonderivatized spruce and birch lignin by H(1) NMR spectroscopy, *Acta Chem. Scand. B* **1981**, *35*, 497-501.

K. Lundquist, A. Paterson and L. Ramsey, NMR studies of lignins. (6). Interpretation of the H(1) NMR spectrum of acetylated spruce lignin in a deuterioacetone solution, *Acta Chem. Scand. B* **1983**, *37*, 734-736.

K. Lundquist and S. von Unge, NMR studies of lignins. (8). Examinations of pyridine- d_5 solutions of acetylated lignins from birch and spruce by H(1) NMR spectroscopy, *Acta Chem. Scand. B* **1986**, *40*, 791-797.